

Madras® by Galvolux

Exclusive decorative glass

Technical data sheet

Millerighe

Base product : float glass to EN 572 1-2.

Description and performance: one side of the plate is chemically and permanently etched so that it partially screens vision whilst allowing light through. Its texture is satin-finish and very slightly in relief with respect to the slightly etched, brilliant ground. Exceptional fingerprint resistance and easy to clean.

The pattern is available parallel to 3210 mm side and to 2250 mm side. Please specify when ordering.

Applications :

Internal applications: doors, partitions walls, furniture, shower screens etc.

External applications: façades, parapets, shelters etc.

Sheet size : 2250 x 3210 mm
(usable 2210 x 3170 mm) - Art. 401239

Thicknesses: monolithic float glass 4/5/6/**8**/10/12 mm

Colours: **extraclear**, clear, bronze, gray.

Availability of standard colours/thicknesses is subject to change. Please verify when ordering.

Bold characters indicate the type of glass in stock.

Weight: 2.5 kg/m² per millimetre of thickness.

Compatible processing: all mechanical and thermal processes compatible with the base material: cutting, grinding, bevelling, drilling, laminating, toughening, bending, double glazing, painting, etc.

Cleaning: care must be taken when installing the glass not to get putty, resin, sealants, etc., on the treated side. Each of these substances requires a specific solvent for removing traces from glass. For routine maintenance, use water and/or any of the commonly marketed glass detergents. Dry immediately with a clean cloth - preferably micro-fibre - by wiping repeatedly gently.



Colours and finishings in the photographs may look slightly different from those of the real products: we recommend that customers examine sample glass before choosing products.

GALVOLUX



QUALITY
AND WARRANTY
SINCE 1900

Galvolux SA

Via Strecce 1 - CH 6934 Bioggio

Tel. +41 91 610 55 11

info@galvolux.com

www.galvolux.com

Madras[®] by Galvolux

Exclusive decorative glass

Millerighe

Defect acceptance limits: for any defect coming from float glass production: as per UNI EN 572.2.
For any defect coming from the chemical processing:

CATEGORY	DEFECT SIZE mm	MAX DEFECT NO. / SHEET	AVERAGE NO. / 20 SMQ
A	> 0,6 and < 1,5	4	6
B	> 1,5 and < 3,0	2	3
C	> 3,0 e < 9,0	Upon customer's acceptance only	Upon customer's acceptance only



Colours and finishings in the photographs may look slightly different from those of the real products: we recommend that customers examine sample glass before choosing products.

GALVOLUX



QUALITY
AND WARRANTY
SINCE 1900

Galvolux SA

Via Strecce 1 - CH 6934 Bioggio

Tel. +41 91 610 55 11

info@galvolux.com

www.galvolux.com