

Madras[®] by Galvolux

Exclusive decorative glass

Technical data sheet

Trix

Base product: float glass to EN 572 1-2.

Description and performance: one side of the plate is chemically and permanently etched so that it partially screens vision whilst allowing light through. Its texture is pleasantly touch-sensitive, thin brilliant lines mark the satin surface. Exceptional fingerprint resistance and easy to clean.

Applications:

Internal: doors, partitions walls, furniture, shower screens etc.

External: façades, parapets, shelters etc.

Sheet size: 2250/2400 x 3210 mm

(useful: 2210/2360 x 3170 mm) - Art. 401238

Pattern length: 3210/2400 mm

Thicknesses: monolithic float glass

4/5/6/**8**/10/12 mm.

Colours: **extraclear**, clear, bronze, grey, green, blue, rose.

Availability of standard colours/thicknesses is subject to change. Please verify when ordering.

Bold type indicates the type of glass in stock.

Weight: 2.5 kg/m² per millimetre of thickness.

Compatible processing: all mechanical and thermal processes compatible with the base material: cutting, grinding, bevelling, drilling, laminating, toughening, bending, double glazing, painting, enamelling etc.

Cleaning: care must be taken when installing the glass not to get putty, resin, sealants. etc., on the treated side. Each of these substances requires a specific solvent for removing traces from glass. For routine maintenance, use water and/or any of the commonly marketed glass detergents. Dry immediately with a clean cloth, preferably micro-fibre.



Colours and finishings in the photographs may look slightly different from those of the real products: we recommend that customers examine sample glass before choosing products.

GALVOLUX



QUALITY
AND WARRANTY
SINCE 1900

Galvolux SA

Via Strecce 1 - CH 6934 Bioggio

Tel. +41 91 610 55 11

info@galvolux.com

www.galvolux.com

Madras[®] by Galvolux

Exclusive decorative glass

Defect acceptance limits: for all defects coming from float glass production: as per UNI EN 572.2 For all defects coming from the chemical processing:

Defect size/mm	Max no./sheet	average per 20 mq
>0,6 e > 1,5	3	5
>1,5 e > 3,0	1	2
>3,0 e > 9,0	only with customer acceptance	only with customer acceptance

Longitudinal pattern deviation tolerance 1 mm/ 1 m.

Trix



Colours and finishings in the photographs may look slightly different from those of the real products: we recommend that customers examine sample glass before choosing products.

GALVOLUX



QUALITY
AND WARRANTY
SINCE 1900

Galvolux SA

Via Strecce 1 - CH 6934 Bioggio

Tel. +41 91 610 55 11

info@galvolux.com

www.galvolux.com